

FOR PROFESSIONAL USE ONLY. Read all applicable and current product information for your project: Technical Data Sheet (TDS), Color Chart, Installation Guide, Material Safety Data Sheet (MSDS).

1. Description: T1000™ Primer is a bonding agent for use with T1000™ Stampable Overlay, a cementitious overlay for the resurfacing of interior or exterior concrete. As an option, it may also be used with T1000 Sprayable Fine Overlay. It is a concentrated ethyl vinyl acetate (EVA) copolymer liquid, that when properly mixed and applied, enhances the adhesion, workability and curing of cementitious overlays. It is a white liquid that dries to a clear film. For interior or exterior and horizontal or vertical use.

2. Packaging: T1000™ Primer is packaged in 1-gallon (3.8L) plastic containers. Containers should be stored in a cool, dry place; protected from freezing, contamination or extended storage in high heat. Do not reuse empty container. Shelf life in properly stored containers is approximately one year.

3. Coverage: Mix a 1-gallon (3.8L) unit 1:1 with clean, cool water. Do not add more water than recommended. Do not mix with other chemicals or alter in any way. Always measure materials to ensure proper dilution ratio. The recommended coverage rate is 400 SF per mixed gallon (39.8 m²/L). Do not pour diluted material back into original container. Two applications are recommended to avoid pinholes in the dried film. Coverage rate will vary depending on surface texture, porosity, application method, air and concrete temperature, wind and humidity.

4. Cautions: May cause eye, skin, and respiratory irritation. Do not take internally. Keep out of reach of children and animals. Wear an organic respirator, eye protection, and clothing during application. Ensure adequate ventilation during and after application. In case of spillage, absorb and dispose of material in accordance with local, state, and federal regulations. Before use, read Material Safety Data Sheet (MSDS).

5. Equipment: *MIXING;* T1000™ Primer may be mixed with a drill mounted paint paddle. Do not introduce air bubbles into diluted product by high speed mixing. Once mixed 1:1, do not add more water.

APPLICATION Apply T1000™ Primer with a short-nap roller, brush, or hand-pump sprayer. If a sprayer is used, material must be worked into the substrate with a brush or roller. The application tools should be clean and dry. If tools become tacky during application, they should be replaced or cleaned with water and free from excess water before using again.

6. Surface Preparation: Clean area and remove all unsound concrete, grease, oil, paint, mastics, and any other materials that will impede penetration and adhesion of the primer or cementitious overlay. Thoroughly roughen and open slick or sealed surfaces. Repair all cracks. Do not attempt to fill or repair cracks with T1000™ Primer. Concrete must be structurally sound. Protect the cleaned and repaired substrate from contamination prior to the application of the primer.

7. Application: Do not apply T1000™ Primer if substrate is damp or frozen. Do not apply when air or substrate temperature is below 45°F (7°C) or above 90°F (32.2°C). Do not apply if primed surface will be exposed to freezing temperatures soon after application. Using a short-nap roller or a long handled brush, evenly and thinly apply primer, thoroughly working it into the substrate. Do not allow primer to accumulate in joints, depressions or puddle, or over apply with one coat. Allow T1000™ Primer to dry 1-3 hours to a clear, tack free film before application of the second coat. High humidity, cool temperature, and non-absorptive surfaces may extend dry time. If possible, apply second coat perpendicular to the first application. Avoid puddling or excessive application.

Once the primer is dry, it must be protected from moisture prior to the application of T1000™ Stampable Overlay or T1000™ Fine Overlay. If the surface becomes wet, primer must be reapplied. Protect the primed surface from dirt or contamination. Also protect the primed surface from contamination with liquid or powdered release agents. T1000™ Stampable Overlay or T1000™ Fine Overlay must be

applied within 24 hours after application of T1000™ Primer. After 24 hours, cleaning the surface and reapplication of the primer may be required before installing the overlay. Clean all mixing and application equipment with soap and water. Do not wash equipment over the primed surface.

8. Quality Control: Cast a job site sample at least 21 days prior to the installation for approval of color and finish. Utilize all materials, tools, and techniques from the actual job in the mock-up. Consistent batching, pouring, finishing, curing, sealing, and preparation techniques, will ensure the uniformity of architectural concrete. Verify adequate wet and dry slip resistance. Verify maintenance requirements.

Warranty Disclaimer/Limitation of Liability: MARSHALLTOWN INC. MAKES NO WARRANTIES REGARDING THIS PRODUCT, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. MARSHALLTOWN ITS DIRECTORS, OFFICERS AND EMPLOYEES SHALL NOT BE LIABLE FOR INDIRECT, SPECIAL OR CONSEQUENTIAL DAMAGES OR PERSONAL INJURY ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT WHETHER OR NOT MARSHALLTOWN INC. HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH A LOSS OR DAMAGE. PURCHASER ASSUMES ALL LIABILITY FOR THE USE AND HANDLING OF THIS PRODUCT INCLUDING ANY INJURY TO THIRD PARTIES. MARSHALLTOWN COLOR'S MAXIMUM LIABILITY SHALL BE THE PRICE OF THE PRODUCT.